

PRODUCT DESCRIPTION

BASIC USE A calcium silicate masonry unit used for masonry veneer construction.

Veneer applications include traditional full-bed masonry installations and thin-clad installations. For thin-clad installations refer to ARRISCRAFT•DATA – Thin-Clad Calcium Silicate Units. For interior and exterior use in residential, commercial and institutional applications.

COMPOSITION AND MATERIAL Renaissance® Masonry Units are manufactured calcium silicate masonry units containing no Portland cement. They are pressure-formed and autoclave cured, resulting in high-density, severe weathering modular masonry units, with one or more finished faces. Refer to ARRISCRAFT•NOTE – Calcium Silicate Masonry Units for further information.

They may be site cut, trimmed and finished to custom lengths, shapes or sizes, as necessitated by site conditions.

SHAPES AND SIZES Renaissance® Masonry Units are available in imperial standard sizes, (Metric sizes are also available from the Cambridge, Ontario manufacturing facility. Ask your local representative for details).

METRIC	HEIGHT	LENGTH	BED	IMPERIAL	HEIGHT	LENGTH	BED
REN09	90 mm	590 mm	90 mm	REN358	3-5/8"	23-5/8"	3-5/8"
REN19	190 mm	590 mm	90 mm	REN758	7-5/8"	23-5/8"	3-5/8"
REN29	290 mm	590 mm	90 mm	REN1158	11-5/8"	23-5/8"	3-5/8"

Renaissance® Masonry Units are also available in custom shapes and sizes, up to a maximum length of 590 mm (23-5/8") and face rise of 290 mm (11-5/8"). Bed depths are limited to a maximum of 90 mm (3-5/8") with rocked faced finishes and 117 mm (4-5/8") with smooth faced finishes. Profiles such as margins, chamfers, notches and bullnoses are available at a premium price. Refer to the Renaissance® Custom Profiles Guide for further information or contact your local Arriscraft representative or dealer.

TOLERANCES Renaissance® Masonry Units are fabricated to the following tolerances:

- Unit Length: ± 1.5 mm ($\pm 1/16$ ")
- Unit Height: ± 1.5 mm ($\pm 1/16$ ")
- Deviations from square, with the measurement taken using the longest edge as the base will be ± 1.5 mm ($\pm 1/16$ ")
- Bed Depth Thickness: ± 3 mm ($\pm 1/8$ ")
- Custom Unit Dimensions: ± 3 mm ($\pm 1/8$ ")

Finished unit heads can be custom ordered or finished on site by the contractor. With Smooth, Sandblasted and Satin finishes, about 15% of units randomly placed on skids come with one acceptable head. Units ordered with finished heads will deviate from the standard dimension. Refer to Table 04230.1.A for the expected deviations when ordering finished heads.

Finish	Number of Finished Heads	Reduction in Unit Length
Dressed	1 • 2	3/8" • 3/4"
Sandblasted	1 • 2	3/8" • 3/4"
Rocked	1 • 2	3/4" • 1-1/2"

Due to the nature of these finishing operations, the custom dimensions tolerance of ± 3 mm ($\pm 1/8$ ") will apply.

A factory applied coating may be present on the long mortar beds of the units. Consider the need to order finished beds for application where they may be exposed.

Units shall exhibit a texture approximately equal to the approved sample when viewed under diffused daylight illumination at a 6 Metre (20 foot) distance. Minor chipping resulting from shipment and delivery shall not be grounds for rejection. Minor chips shall not be obvious under diffused daylight illumination from a 6 Metre (20 foot) distance.

Units being provided with rusticated faces are inspected for cracks and blemishes only,

as chippage considerations do not apply when the desired surface texture and unit shape is intended to be uneven.

LIMITATIONS Manufactured masonry products are generally intended for above grade installations. All manufactured masonry units, regardless of their composition, are inherently absorptive, and none are intended for use below grade. Units installed below grade will wick moisture from the soil that is in contact with the masonry units and create a condition known as "rising damp" in the masonry veneer.

In colder climates, masonry walls at grade may become exposed to de-icing compounds. Like all types of manufactured masonry units, calcium silicate masonry units should not be installed where they will be directly exposed to de-icing compounds used to melt snow and ice from pavements. For information about installing masonry at grade refer to the "At Grade design Ideas" brochure.

The function of caps and copings is to prevent moisture from entering the building envelope through the top of the wall. As most manufactured masonry units are produced in relatively short lengths, if they are used as a cap or coping material, more mortar joints are required between the individual units. These mortar joints are the most likely entry points for moisture to infiltrate the building envelope. As such, it is generally recommended within the industry that longer components, such as quarried stone or metal parapet cap flashing be used to reduce the number of joints thereby limiting the areas that may allow moisture infiltration of the building envelope.

COLOURS AND FINSHES Renaissance® Masonry Units are available from our Cambridge, Ontario manufacturing facility in standard colours and finishes listed in Table 04230.2.A.

	Colours	Finish		
		Sandblasted	Rocked	Corduroy
Monochromatic	Wheat	•	•	•
	White	•	•	•
	Monochromatic colours consist of a single hue.			
Monochromatic Range	Carbon	•	•	•
	Monochromatic range colors consist of a single hue with a subtle distribution of tones that vary from unit to unit.			
Striated	Nutmeg	•	•	•
	Striated colours are a multi-hue blend.			
Range	Barnwood	•	•	•
	Birchbark	•	•	•
	Driftwood	•	•	•
	Ryegrass	•	•	•
	Ironstone	•	•	•
	Sandrift	•	•	•
For those colours designated as Range, the distribution of colours or shades will vary from unit to unit.				

Refer to actual colour samples and panels for final colour selection.

Custom colours are also available on a minimum order basis. Contact your local Arriscraft representative or dealer for additional information.

These standard finishes are described below:

- Sandblasted Finish: A matte textured, relatively fine-grained uniform smooth surface.
- Rocked Finish: A bold rustic finish resulting from hand-chiseling the masonry unit to a set bed depth.
- Dressed Finish: A smooth finish which exposes any inherent mottled colouring of the unit. Visible finishing marks in a circular pattern are considered acceptable.

As a manufactured product, Renaissance® Masonry Units are monitored for colour consistency. Slight variations between batches may occur and it is recommended that the installer mix units from different skids during installation. Consultants should review samples prior to selecting a particular colour and finish.

TECHNICAL DATA

APPLICABLE STANDARDS Required properties for calcium silicate masonry are described in ASTM C73, Standard Specification for Calcium Silicate Face Brick (Sand-Lime Brick).

This standard classifies calcium silicate products as either moderate-weathering or severe-weathering depending on the material's tested physical properties of compressive strength and 24-hour absorption. Renaissance® Masonry Units meet the severe weathering requirements of this standard.

INSTALLATION

DELIVERY - Renaissance® Masonry Units are delivered to the site in protective packaging.

HANDLING - Lift skids with proper and sufficiently long slings or forks with protection to prevent damage to units. Protect edges and corners.

Storage - Store Renaissance® Masonry Units in a manner designed to prevent damage and staining of units. Stack units on timbers or platforms at least 76 mm (3") above grade. Place polyethylene or other plastic film between wood and other finished surfaces of units when stored for extended periods of time. Stored units should be covered if exposed to extreme weather conditions. Do not use de-icing compounds to remove ice from masonry surfaces.

PREPARATORY WORK - It may be advantageous under hot, dry weather or windy conditions to pre-dampen the units prior to placement in the wall. Damp units should be surface dry at the time of placement. For additional information when constructing in hot or cold weather refer to the ARRIS-CRAFT•TECH bulletins titled Hot Weather Masonry Construction and Cold Weather Masonry Construction.

INSTALLATION Renaissance® Masonry Units must be installed using approved materials and techniques for each specific installation.

Construct masonry veneer with an adequate number of elastic movement joints, properly located to accommodate differential movement. Refer to ARRIS-CRAFT•NOTE – Building Movement Joints for further information.

Construct masonry veneer in accordance with CSAA371: Masonry Construction for Buildings and any local requirements stipulated by the authorities having jurisdiction.

Mortar joints between units in any direction should be 10 mm (3/8") thick. Mortar for unit masonry veneer should be a Type N Portland cement-lime mix, proportioned to a 1:1:6 ratio.

- 1 part Portland cement (CSAA3001, Type GU)

- 1 part hydrated lime (CSA C207, Type S - Special); and
- 6 parts masonry sand (CSAA179-14)

When properly combined with the appropriate quantity of water, it will produce a general-purpose mortar, exhibiting good workability and board life in its plastic state, and good durability and flexibility in its hardened state; and conforming to CSA A179-14 - Mortar and Grout for Unit Masonry. For Further information, refer to ARRIS-CRAFT•NOTE – Mortar for Masonry Veneer.

Arriscraft recommends construction masonry veneer with proper drainage mechanisms, including clear draining air spaces, through wall flashing membranes and weep hold vents. The air spaces must be at least 1" wide, and kept clear of debris, protrusions, mortar fins and droppings. Weep hold vents should be installed at the same level as through wall flashing membranes and spaced not more than 24" on centre horizontally. Refer to ARRIS-CRAFT•NOTE – Moisture Management for further information.

Renaissance® Masonry Units must be connected to a structural substrate with an approved masonry connection system, designed by the consultant for each specific installation. Refer to ARRIS-CRAFT•NOTE – Connectors – Part I, Masonry Ties.

AVAILABILITY AND COST

AVAILABILITY Renaissance® Masonry Units are available worldwide.

Delivery times for orders will vary based on the complexity of what is required.

Arriscraft cannot be responsible for delays due to fire, acts of God, or any other cause beyond its control or which could not be reasonably foreseen.

Contact Arriscraft for a list of dealers in your area.

COST Quoted on a project basis for job-specific manufacturing to project requirements.

WARRANTY

Arriscraft warrants its products against deterioration for the life of the building, provided the products have been erected and used according to accepted masonry standards, within the guidelines of local building codes and as recommended by the manufacture. Complete warranty information is outlined on the Arriscraft standard form of Product Warranty.

MAINTENANCE

Renaissance® Masonry Units should have excess mortar removed from their faces by brushing as they are placed within the wall at the point of tooling. Clean Renaissance® Masonry Units in accordance with the cleaning guidelines in ARRIS-CRAFT•CARE. Some masonry detergents and cleaning systems can change the colour of masonry products. Acid-based cleaning agents will darken the colour of the masonry units.

Always pre-test cleaning agents and methods on the job-site mock-up panel or a small inconspicuous area of the wall. The Consultant and /or Owner should approve the test area prior to the start of full-scale cleaning operations.

Refer to ARRIS-CRAFT•CARE – Cleaning Guidelines and ARRIS-CRAFT•NOTE – Cleaning Masonry for further information. Arriscraft does not recommend the application of water repellent or graffiti-proofing sealers to its masonry products.

TECHNICAL SERVICES

Arriscraft offers consultation services to assist with the preparation of details, specifications and with pricing. Enquiries are addressed promptly and without obligation.

RELATED REFERENCES

Arriscraft distributes an integrated technical information system including:

- ARRIS-CRAFT•CADD: sample details which are available in .dwg, .dxf, and .pdf formats.
- ARRIS-CRAFT•DATA: product data sheets.
- ARRIS-CRAFT•NOTE: technical discussions with respect to building construction issues
- ARRIS-CRAFT•SPEC: master guide specification sections.

All of these technical resources are available to be downloaded from the Arriscraft web site at www.arriscraft.com.

Arriscraft also makes available samples for colour and finish, coursing charts and copies of test reports upon request.

